



TECHNICAL DATA SHEET FOR

NIPPON ROAD LINE PAINT

DESCRIPTION : It is tough, fast-drying and weather-durable coat formulated to

withstand wear for road and floor marking

TYPE : Modified chlorinated rubber resin with thermoplastic property

COLOUR : White, Yellow (537 of BS 381C), Red and Black

FINISH : Matt

USES : For coating on

Concrete Floor

Asphalt

Plastered Wall

FEATURES : • Excellent eye visibility

Hard and abrasive resistant

Very fast dryingWeather resistant

APPLICATION DATA

METHOD : Roller, brush and air and airless spray

THEORETICAL COVERAGE: 10 m² / litre (based on 40 microns DFT per coat)

DILUTION : Use Nippon Road Line Paint Reducer

Brush - 10% max
Roller - 10% max
Air Spray - 10%-20%
Airless Spray - 0%-5%

SURFACE PREPARATION: The surface must be clean, dry and free from grease /oil and any

other foreign matter.

Painting System

Recommended two coats with minimum dry film thickness of 40

microns each for optimum performance.

SPRAY APPLICATION : Air Airless

 Delivery Pressure(kg/cm²)
 3 - 4
 140 - 170

 Tip size 60° angle
 1.3mm
 0.017"

 Dilution
 10-20%
 0-5%

TECHNICAL DATA SHEET FOR

NIPPON ROAD LINE PAINT

DRYING TIME : Touch Dry - 5 mins at 30° C

OVERCOATING TIME : 1 hour in normal conditions

CLEANING : All equipment should be cleaned with NIPPON ROAD LINE PAINT

REDUCER immediately after use.

GENERAL INFORMATION

CONFORMITY Nippon Road Line Paint (White, Yellow & Red) is certified under TÜV

SÜD PSB Product Listing Scheme to SS 221:2002

SOLID CONTENT : $62 \pm 2\%$ by weight (based on white)

SPECIFIC GRAVITY : 1.33 ± 0.03 kg/litre (based on white)

FLASH POINT : 7 °C (for White, Yellow & Red)

23 °C (for Black)

PACKING : 5 litres

STORAGE : Store in a tightly sealed container in a cool and dry place

SHELF LIFE : Up to 24 months when stored in a tightly sealed container

PRECAUTION : Contain volatile solvents, keep away from naked flame.

Avoid direct contact with skin. Use appropriate protection equipment.

Refer to the product Safety Data Sheet for more information.

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details : Customer Service

6265 5355 (Main Line) 6264 1603 (Fax)

www.nipponpaint.com.sg